









QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	$E \leq 0.1\% \text{ Bl aGL}$
 <b>Breaking strength</b>	ISO 10545-4	Modulus of Rupture Breaking of Rupture	$R \geq 35 \text{ N/mm}^2$ $S \geq 1300 \text{ N}$
 <b>Abrasion resistance</b>	ISO 10545-7	Resistance to Surface Abrasion of Glazed Tiles MOHS	Class 3 - All Other Colors Class 4 - Cloud White
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Frost Proof
 <b>Chemical resistance</b>	ISO 10545-13	Resistance to Household Chemicals Resistance to Low Concentrations of Acids + Bases	Class A Class LA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	DCOF	$\geq 0.42$
 <b>Shade Variation</b>	See Below	Moderate Variation	V3



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

FOR THE BEST PRODUCT LAYING RESULTS, MATERIAL FROM AT LEAST THREE BOXES SHOULD BE MIXED