









# HYDE PARK PENTA - 2"x2" GLOSSY & IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	4
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137.1	< 0.42
 <b>Shade Variation</b>	See Below	Substantial Variation	V4

**Colors Featured in Hyde Park Penta 2"x2" Glossy & Iridis Finish:**

· Amalfi · Bari · Cayo Coco · Tanzanite · Umbria · Verona ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)

# HYDE PARK PENTA - 2"x2" GLOSSY

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	4
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137.1	< 0.42
 <b>Shade Variation</b>	See Below	Substantial Variation	V4

### Colors Featured in Hyde Park Penta 2"x2" Glossy Finish:

· Forest Blue · Iria · Kara Blue · Lungomare · Print · Saona · Tozen ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)

# HYDE PARK PENTA - 2"X2" MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	5
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137.1	0.62
 <b>Shade Variation</b>	See Below	Slight Variation	V2

**Colors Featured in Hyde Park Penta 2"X2" Matte Finish:**

· Matte Black Rock · Matte Ivet ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)

# HYDE PARK PENTA - 2"x2" SATIN IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	5
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137.1	≥ 0.42
 <b>Shade Variation</b>	See Below	Substantial Variation	V4

### Colors Featured in Hyde Park Penta 2"x2" Satin & Iridis Finishes:

· Satin Dance Iridis ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)

# HYDE PARK PENTA - 2"x2" SATIN

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	4
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137.1	≥ 0.42
 <b>Shade Variation</b>	See Below	Substantial Variation	V4

**Colors Featured in Hyde Park Penta 2"x2" Satin Finish:**

· Arlet · Bittor · Carel · Eloa · Yadel ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)