









| QUALITY CHARACTERISTICS   | NORM         | STANDARDS   | RESULT     |
|---|--------------|---|------------|
|  <b>Water absorption of the body</b>     | ISO 10545-3  | ≤ 0.5%  | Conformity |
|  <b>Breaking strength</b>                | ISO 10545-4  | ≥ 35 N/mm <sup>2</sup>  | Conformity |
|  <b>Abrasion resistance</b>              | ISO 10545-7  | PEI   | PEI 4      |
|  <b>Frost resistance</b>                 | ISO 10545-12 | No samples must show ruptures or noticeable surface alteration. | Conformity |
|  <b>Chemical resistance</b>              | ISO 10545-13 |   | GA GLA     |
|  <b>Thermal shock resistance</b>         | ISO 10545-5  |   | Conformity |
|  <b>Dynamic coefficient of friction</b> | BOT 3000E    | DCOF ≥ 0.42   | 0.48       |
|  <b>Slight Variation</b>               | See Below    |   | V3         |

**SIZES FEATURED IN THE MATTE FINISH:**

- 8" x 8" and 8.79" x 9.9" Hexagon -



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4

*For the best product laying results, material from at least three boxes should be mixed.*

**CERAMICHE  D'ARTE**

[www.bfceramics.com](http://www.bfceramics.com)