









HYDE PARK PENNY ROUND GLOSSY & IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137-1	N/A
 Shade Variation	See Below	Substantial Variation	V4

Colors Featured in Hyde Park Penny Round Glossy & Iridis Finish:

Amalfi, Bari, Cayo Coco, Tanzanite, Umbria, Verona

For the best product laying results, material from at least three boxes should be mixed.



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3











Substantial Variation

V4

HYDE PARK

www.bfceramics.com

HYDE PARK PENNY ROUND GLOSSY

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	N/A
 Shade Variation	See Below	Slight to Substantial Variation	See Below

Colors Featured in Hyde Penny Round Glossy Finish:

Forest Blue, Iria, Kara Beige, Kara Blue, Lungomare, Nordic Stone, Print, Saona, Shiny Black, Shiny Dark Grey, Shiny Grey, Shiny Taupe, Shiny White, Tozen

Shade Variation (V2)

Shiny Black, Shiny Dark Grey, Shiny Grey, Shiny Taupe, Shiny White

Shade Variation (V4)

Forest Blue, Iria, Kara Beige, Kara Blue, Lungomare, Nordic Stone, Print, Saona, Tozen



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com

HYDE PARK PENNY ROUND IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	N/A
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Penny Round Iridis Finish:

Opalo Black, Opalo White

For the best product laying results, material from at least three boxes should be mixed.



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3











Substantial Variation

V4

HYDE PARK

www.bfceramics.com

HYDE PARK PENNY ROUND MATTE & IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	N/A
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Penny Round Matte & Iridis Finish:

Nature Glass Opalo Black, Natura Glass Opalo White

For the best product laying results, material from at least three boxes should be mixed.



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3











Substantial Variation

V4

HYDE PARK

www.bfceramics.com

HYDE PARK PENNY ROUND MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	5
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	See Below
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Penny Round Matte Finish:

Abuhna Matte, Arabescato Gold Matte, Beray Matte, Brescia Matte, Calacatta Gold Matte, Fosco Matte, Grafito Matte, Matte Black Rock, Matte Ivet, Normatech Antracite Matte, Normatech Dark Taupe Matte, Normatech Grey Matte, Normatech Ivory Matte, Normatech Sand Matte, Shabby Terra Matte, Yada Matte

Dynamic Coefficient of Friction Colors:

0.42: Abuhna Matte, Calacatta Gold Matte, Fosco Matte, Grafito Matte, Shabby Terra Matte, Yada Matte

0.60: Arabescato Gold Matte, Beray Matte, Brescia Matte, Matte Black Rock, Matte Ivet, Normatech Antracite Matte, Normatech Dark Taupe Matte, Normatech Grey Matte, Normatech Ivory Matte, Normatech Sand Matte



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com

HYDE PARK PENNY ROUND SATIN

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	5
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137-1	0.42
 Shade Variation	See Below	Substantial Variation	V4

Colors Featured in Hyde Park Penny Round Satin Finish:

Arlet, Bittor, Carel, Danae, Eloa, Yadel

For the best product laying results, material from at least three boxes should be mixed.



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4

HYDE PARK

www.bfceramics.com