









QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	0.5% < E <= 3% (Bib)
 Breaking strength	ISO 10545-4	ISO 10545-4	>30N/mm ²
 Abrasion resistance	ISO 10545-7		Class 0
 Frost resistance	ISO 10545-12	ISO 10545-12	Complies
 Chemical resistance	ISO 10545-13	Household Chemicals Acids (Low Concentration)	GA (no effect) GLA (no effect)
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Complies
 Dynamic coefficient of friction	BOT 3000E	Not Applicable; Wall Tile Only	
 Slight Variation	See Below	Moderate Variation	V3



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

FOR THE BEST PRODUCT LAYING RESULTS, MATERIAL FROM AT LEAST THREE BOXES SHOULD BE MIXED

