









| QUALITY CHARACTERISTICS | NORM | STANDARDS | RESULT |
|---|-----------------|---|--|
|  Water absorption of the body | ISO 10545-3 | ≤ 0.5% | 0.1% |
|  Breaking strength | ISO 10545-4 | > 35N - 45 N / mm ² > 1600 - 2400 N | 45-60 N / mm ² 1801-2500 N |
|  Abrasion resistance | ISO 10545-7 | < 130 mm ² | Class 2: Graphite, Greige Class 3: Silver Class 4: White |
|  Frost resistance | ISO 10545-12 | ISO 10545-12 | Resists |
|  Chemical resistance | ISO 10545-13 | Acids and Basis Cleaning Products + Pool Agents - Minimum UB | Conforms Class UA |
|  Thermal shock resistance | ISO 10545-9 | ISO 10545-9 | Resists |
|  Dynamic coefficient of friction | BOT 3000E | ANSI A326.3 | 0.70 |
|  Shade Variation | See Below | Slight Variation | V2 |



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4









Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

TAU

ceramica

www.bfceramics.com

| QUALITY CHARACTERISTICS | NORM | STANDARDS | RESULT |
|---|-----------------|---|--|
|  Water absorption of the body | ISO 10545-3 | ≤ 0.5% | 0.1% |
|  Breaking strength | ISO 10545-4 | > 35 - 45 N/ mm ² > 1600-2400 N | 45-60 N / mm ² 1800-2500 N |
|  Abrasion resistance | ISO 10545-7 | < 130 mm ² | Class 2: Graphite, Greige Class 3: Silver Class 4: White |
|  Frost resistance | ISO 10545-12 | ISO 10545-12 | Resists |
|  Chemical resistance | ISO 10545-13 | Acids and Basis Cleaning Products + Pool Agents - Minimum UB | Conforms Class UA |
|  Thermal shock resistance | ISO 10545-9 | ISO 10545-9 | Resists |
|  Dynamic coefficient of friction | BOT 3000E | | |
|  Shade Variation | See Below | Slight Variation | V2 |



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

TAU

ceramica

www.bfceramics.com