









CORRADO STONE MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	≤ 0.5%	Conformity
 Breaking strength	ISO 10545-4	≥ 35 N / mm ²	Conformity
 Abrasion resistance	ISO 10545-7	PEI	4 - Blue Stone 5 - All Other Colors
 Frost resistance	ISO 10545-12	No Samples Must Show Ruptures Or Noticeable Surface Alteration	Conformity
 Chemical resistance	ISO 10545-13	ISO 10545-13	GA GLA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Conformity
 Dynamic coefficient of friction	BOT 3000E		> 0.54
 Shade Variation	See Below		V2 - Blue Stone V3 - All Other Colors



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

Test values are based on ANSI/ISO standards according to: ANSI A137.1-Porcelain Tile P1 CLASS, ISO 13006-G-BIA Group, EN14411-G-BIA Group. Variances in test values can occur in different production lots.

CERAMICHE D'ARTE

www.bfceramics.com