









QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	Average Value (%)	≤ 0.5 %
 Breaking strength	ISO 10545-4	Breaking Strength (N) N/mm ²	1.600-2.400N 35-45N/mm ²
 Abrasion resistance	ISO 10545-7		PEI 3 : Gris PEI 4 : Bone
 Frost resistance	ISO 10545-12		Resists
 Chemical resistance	ISO 10545-13	Ammonium Chloride 100 g/l Sodium Hypochlorite 20 mg/l Hydrochloric Acid 3% Citric Acid 100 g/l	A A Compiles with Standard Compiles with Standard
 Thermal shock resistance	ISO 10545-5		
 Dynamic coefficient of friction	BOT 3000E	ANSI A326.3	Bone = 0.45 Gris = 0.49
 Shade Variation	See Below		V4



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

Test values are based on ANSI/ISO standards according to: ANSI A137.1-Porcelain Tile P1 CLASS, ISO 13006-G-BIA Group, EN14411-G-BIA Group. Variances in test values can occur in different production lots.

TAU

cerámica

www.bfceramics.com