









TERMA FLOOR & WALL / MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	UNE EN ISO 10545-3	E ≤ 0.5
 Breaking strength	ISO 10545-4	UNE EN ISO 10545-4	> 1300 N ≥ 35N / mm ²
 Abrasion resistance	ISO 10545-7	UNE EN ISO 10545-7	PEI 4
 Frost resistance	ISO 10545-12	UNE EN ISO 10545-12	Complies
 Chemical resistance	ISO 10545-13	Resistance to home cleaning products and swimming pool salts Resistance to high concentration acids and bases Resistance to low concentration acids and bases	Class A Minimum HB Minimum LB
 Thermal shock resistance	ISO 10545-9	UNE EN ISO 10549-9	Complies
 Dynamic coefficient of friction	BOT 3000E	ANSI A 326.3-2021	0.60
 Shade Variation	See Below		V3



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation









For the best product laying results, material from at least three boxes should be mixed.

Test values are based on ANSI/ISO standards according to: ANSI A137.1-Porcelain Tile P1 CLASS, ISO 13006-G-BIA Group, EN14411-G-BIA Group. Variances in test values can occur in different production lots.

ARGENTA

www.bfceramics.com

TERMA WALL / MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	UNE EN ISO 10545-3	E > 10%
 Breaking strength	ISO 10545-4	UNE EN ISO 10545-4	> 200 N ≥ N / mm ²
 Abrasion resistance	ISO 10545-7	UNE EN ISO 10545-7	PEI 1
 Frost resistance	ISO 10545-12	UNE EN ISO 10545-12	Not Resistant
 Chemical resistance	ISO 10545-13	Resistance to home cleaning products and swimming pool salts Resistance to high concentration acids and bases Resistance to low concentration acids and bases	Class A Minimum HB Minimum LB
 Thermal shock resistance	ISO 10545-9	UNE EN ISO 10549-9	Complies
 Dynamic coefficient of friction	BOT 3000E	Not Applicable - Wall Tile Only	
 Shade Variation	See Below		V3



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

Test values are based on ANSI/ISO standards according to: ANSI A137.1-Porcelain Tile P1 CLASS, ISO 13006-G-BIA Group, EN14411-G-BIA Group. Variances in test values can occur in different production lots.

ARGENTA

www.bfceramics.com