









HYDE PARK PENNY ROUND GLOSSY & IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137-1	< 0.42
 Shade Variation	See Below	Substantial Variation	V4

Colors Featured in Hyde Park Penny Round Glossy & Iridis Finishes:

· Amalfi · Bari · Cayo Coco · Tanzanite · Umbria · Verona ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com

HYDE PARK PENNY ROUND GLOSSY

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	< 0.42
 Shade Variation	See Below	Slight to Substantial Variation	See Below

Colors Featured in Hyde Penny Round Glossy Finish:

- Forest Blue · Iria · Kara Beige · Kara Blue · Lungomare · Nordic Stone · Print · Saona · Shiny Black · Shiny Dark Grey · Shiny Grey · Shiny Taupe · Shiny White · Tozen ·

Shade Variation (V2)

- Shiny Black · Shiny Dark Grey · Shiny Grey · Shiny Taupe · Shiny White ·

Shade Variation (V4)

- Forest Blue · Iria · Kara Beige · Kara Blue · Lungomare · Nordic Stone · Print · Saona · Tozen ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com

HYDE PARK PENNY ROUND IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	< 0.42
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Penny Round Iridis Finish:

· Opalo Black · Opalo White ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com

HYDE PARK PENNY ROUND MATTE & IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	< 0.42
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Penny Round Matte & Iridis Finishes:

· Nature Glass Opalo Black · Nature Glass Opalo White ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com

HYDE PARK PENNY ROUND MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	5
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	0.54
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Penny Round Matte Finish:

· Matte Black Rock · Matte Calacatta Gold · Matte Fosco · Matte Grarito · Matte Ivet ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com

HYDE PARK PENNY ROUND SATIN

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137-1	≥ 0.42
 Shade Variation	See Below	Substance Variation	V4

Colors Featured in Hyde Park Penny Round Satin Finish:

· Arlet · Bittor · Carel · Danae · Eloa · Yadel ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com