









QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ANSI/ISO-(%)	$10\% \leq E \leq 18\text{-P4}$
 <b>Breaking strength</b>	ISO 10545-4	ANSI-(lbf) ISO-(N)	$\geq 230$ $> 1000$
 <b>Abrasion resistance</b>	ISO 10545-7	ANSI/ISO	Class 0
 <b>Frost resistance</b>	ISO 10545-12	ANSI/ISO	Not Resistant
 <b>Chemical resistance</b>	ISO 10545-13	ANSI/ISO	Class B
 <b>Thermal shock resistance</b>	ISO 10545-5		
 <b>Dynamic coefficient of friction</b>	BOT 3000E	Not Applicable - Wall Tile Only	
 <b>Shade Variation</b>	See Below		V3



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation












V4

Substantial Variation

*For the best product laying results, material from at least three boxes should be mixed.*

*The polished finish is recommended for wall coverings or for the floors of residential bathrooms. Specifically, floor coverings in this material must not be subjected to excessively heavy traffic and must never be in direct contact with outdoor areas. As is often the case with natural stones, any spots on the surface or any unevenness in shine are typical characteristics of the product, deriving from the process used.*



QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ANSI/ISO-(%)	< 0.5%
 <b>Breaking strength</b>	ISO 10545-4	ANSI-(lbf) ISO-(N)	≥ 400 > 1750
 <b>Abrasion resistance</b>	ISO 10545-7	ANSI/ISO	Class 4
 <b>Frost resistance</b>	ISO 10545-12	ANSI/ISO	Pass
 <b>Chemical resistance</b>	ISO 10545-13	ANSI/ISO	Class A
 <b>Thermal shock resistance</b>	ISO 10545-5		
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI-DCOF (wet) ISO-R Value	Matte ≥ 0.55 Matte R (-)
 <b>Shade Variation</b>	See Below		V3



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

*For the best product laying results, material from at least three boxes should be mixed.*

