









# HYDE PARK PENNY ROUND GLOSSY & IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	4
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137-1	< 0.42
 <b>Shade Variation</b>	See Below	Substantial Variation	V4

**Colors Featured in Hyde Park Penny Round Glossy & Iridis Finish:**

· Amalfi · Bari · Cayo Coco · Tanzanite · Umbria · Verona ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)

# HYDE PARK PENNY ROUND GLOSSY

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	4
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137.1	< 0.42
 <b>Shade Variation</b>	See Below	Slight to Substantial Variation	See Below

### Colors Featured in Hyde Penny Round Glossy Finish:

· Forest Blue · Iria · Kara Beige · Kara Blue · Lungomare · Nordic Stone · Print ·  
· Saona · Shiny Black · Shiny Dark Grey · Shiny Grey · Shiny Taupe · Shiny White · Tozen ·

### Shade Variation (V2)

· Shiny Black · Shiny Dark Grey · Shiny Grey ·  
· Shiny Taupe · Shiny White ·

### Shade Variation (V4)

· Forest Blue · Iria · Kara Beige · Kara Blue · Lungomare ·  
· Nordic Stone · Print · Saona · Tozen ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)

# HYDE PARK PENNY ROUND IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	4
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137.1	< 0.42
 <b>Shade Variation</b>	See Below	Slight Variation	V2

### Colors Featured in Hyde Park Penny Round Iridis Finish:

· Opalo Black · Opalo White ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)

# HYDE PARK PENNY ROUND MATTE & IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	4
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137.1	< 0.42
 <b>Shade Variation</b>	See Below	Slight Variation	V2

**Colors Featured in Hyde Park Penny Round Matte & Iridis Finish:**

· Nature Glass Opalo Black · Nature Glass Opalo White ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)

# HYDE PARK PENNY ROUND MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	5
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137.1	≥ 0.54
 <b>Shade Variation</b>	See Below	Slight Variation	V2

**Colors Featured in Hyde Park Penny Round Matte Finish:**

· Matte Black Rock · Matte Calacatta Gold · Matte Fosco · Matte Grarito · Matte Ivet ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)

# HYDE PARK PENNY ROUND SATIN

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	ISO 10545-3	None
 <b>Breaking strength</b>	ISO 10545-4		
 <b>Abrasion resistance</b>	ISO 10545-7	MOHS	5
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A 137-1	≥ 0.42
 <b>Shade Variation</b>	See Below	Substantial Variation	V4

**Colors Featured in Hyde Park Penny Round Satin Finish:**

· Arlet · Bittor · Carel · Danae · Eloa · Yadel ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4

*For the best product laying results, material from at least three boxes should be mixed.*

# HYDE PARK

[www.bfceramics.com](http://www.bfceramics.com)