









HYDE PARK BRICK - 1"x2" GLOSSY

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	< 0.42
 Shade Variation	See Below	Substantial Variation	V4

Colors Featured in Hyde Park Brick 1"x2" Glossy Finish:

- Amalfi · Bari · Cayo Coco · Forest Blue · Iria · Kara Beige · Kara Blue ·
- Lungomare · Print · Saona · Tanzanite · Tozen · Umbria · Verona ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.


HYDE PARK

www.bfceramics.com

HYDE PARK BRICK - 1"x2" MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	5
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	≥ 0.62
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Brick 1"x2" Matte Finish:
· Matte Black Rock · Matte Ivet ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com