









| QUALITY CHARACTERISTICS | NORM | STANDARDS | RESULT |
|---|-----------------|--------------------------------|-----------------------------|
|  Water absorption of the body | ISO 10545-3 | ANSI/ISO-(%) | < 0.5% |
|  Breaking strength | ISO 10545-4 | ANSI-(lbf) ISO-(N) | ≥ 400 > 1750 |
|  Abrasion resistance | ISO 10545-7 | ANSI/ISO | Class 4 |
|  Frost resistance | ISO 10545-12 | ANSI/ISO | Pass |
|  Chemical resistance | ISO 10545-13 | ANSI/ISO | Class A |
|  Thermal shock resistance | ISO 10545-5 | | |
|  Dynamic coefficient of friction | BOT 3000E | ANSI-DCOF (wet) ISO-R Value | Matte ≥ 0.55 Matte R (-) |
|  Shade Variation | See Below | | V3 |



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

