









QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	< 0.5 %	0.1%
 Breaking strength	ISO 10545-4	> 35 N / mm ² > 1300 N	35-45 N / mm ² 1800 - 2500 N
 Abrasion resistance	ISO 10545-7		
 Frost resistance	ISO 10545-12	ISO 10545 - 12	Resists
 Chemical resistance	ISO 10545-13	Acids and Bases Minimum GB	Conforms Class GA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resists
 Dynamic coefficient of friction	BOT 3000E		
 Shade Variation	See Below		V2



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

For the best product laying results, material from at least three boxes should be mixed.

MARINA BAY

www.bfceramics.com