









# CLADDING MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	E ≤ 10%	E ≤ 15-16%
 <b>Breaking strength</b>	ISO 10545-4	> 1300 N	2600 N
 <b>Abrasion resistance</b>	ISO 10545-7	PEI	1
 <b>Frost resistance</b>	ISO 10545-11	Required	Resists
 <b>Chemical resistance</b>	ISO 10545-13	Resistance to Household Chemicals and Swimming Pool Salts Resistance to Low Concentrations Resistance to High Concentrations	GA GLA GHA
 <b>Thermal shock resistance</b>	ISO 10545-9	Required	Resists
 <b>Dynamic coefficient of friction</b>	BOT 3000E	Not Applicable - Wall Tile Only	
 <b>Shade Variation</b>	See Below		V2



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

*For the best product laying results, material from at least three boxes should be mixed.*

*Test values are based on ANSI/ISO standards according to: ANSI A137.1-Non-Vitreous P4 Class, ISO 13006-L Group; EN14411-L Group. Variances in test values can occur in different production lots.*

**Colorker®**

[www.bfceramics.com](http://www.bfceramics.com)