









QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	Eb > 10%	18% ≤ Eb < 20%
 <b>Breaking strength</b>	ISO 10545-4	>12 N/mm <sup>2</sup>	≥ 13 N/mm <sup>2</sup>
 <b>Abrasion resistance</b>	ISO 10545-7	ISO 10545-7	Class 0
 <b>Frost resistance</b>	ISO 10545-12	ISO 10545-12	Not Resistant
 <b>Chemical resistance</b>	ISO 10545-13	Low Acid and Base Concentrations Resistance to Acids and Alkalis of High Concentration Household Chemicals and Swimming Pool Additives	GLA NPD GA
 <b>Thermal shock resistance</b>	ISO 10545-9	ISO 10545-9	Resistant
 <b>Dynamic coefficient of friction</b>	BOT 3000E	Not Applicable; Wall Tile Only	Not Applicable
 <b>Shade Variation</b>	See Below	Slight Variation	V2



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

FOR THE BEST PRODUCT LAYING RESULTS, MATERIAL FROM AT LEAST THREE BOXES SHOULD BE MIXED



[www.bfceramics.com](http://www.bfceramics.com)