









# BEACH WOOD MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 <b>Water absorption of the body</b>	ISO 10545-3	≤ 0.5%	0.05%
 <b>Breaking strength</b>	ISO 10545-4	≥ 35N/mm <sup>2</sup>	50N/mm <sup>2</sup>
 <b>Abrasion resistance</b>	ISO 10545-7	UNE EN ISO 10545-7:99	Class 3 - Dark Colors
 <b>Frost resistance</b>	ISO 10545-12	UNI EN ISO 10545-12	Resistant
 <b>Chemical resistance</b>	ISO 10545-13	UNI EN ISO 10545-13	Resistant/GLA
 <b>Thermal shock resistance</b>	ISO 10545-5	≥ 1300 N	2,200 N
 <b>Dynamic coefficient of friction</b>	BOT 3000E	ANSI A137.1 BOT 3000	DCOF ≥ 0.42
 <b>Variation</b>	See Below	ANSI A137.1	V3



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation

*For the best product laying results, material from at least three boxes should be mixed.*



[www.bfceramics.com](http://www.bfceramics.com)