









HYDE PARK HEXAGON - 1" MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	See Below
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	See Below
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park 1" Hexagon Matte Finish:

· Emma · Matte Black Rock · Matte Calacatta · Matte Crema Marfil · Matte Ivet · Matte Marquina ·
· Matte Misty · Matte Venato White · Umber · Zement Grey ·

Abrasion Resistance Colors:

4: Emma, Umber, Zement Grey
5: All Remaining Colors

Dynamic Coefficient of Friction Colors:

> 0.42: Emma, Umber, Zement Grey
≥ 0.62: All Remaining Colors



V1

Uniform appearance



V2

Slight Variation



V3

Moderate Variation



V4

Substantial Variation









For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com



HYDE PARK HEXAGON - 1" MATTE, IRIDIS & STONE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	< 0.42
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Hexagon 1" Matte, Iridis & Stone Finish:

· Blend Fossil · Blend Shadow ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4









For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com



HYDE PARK HEXAGON PATTERNS - 1" MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	5
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	≥ 0.62
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Hexagon 1" Pattern Blends Matte Finish:

· Blend Pattern 1 · Blend Pattern 2 · Blend Pattern 3 · Blend Pattern 4



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com

HYDE PARK HEXAGON - 1" SATIN

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	5
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	≥ 0.42
 Shade Variation	See Below	Substantial Variation	V4

Colors Featured in Hyde Park Hexagon 1" Satin Finish:

· Arlet · Bittor · Carel · Danae · Eloa · Yadel ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4









For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com



HYDE PARK HEXAGON - 2" GLOSSY & MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137-1	< 0.42
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Hexagon 2" Glossy & Matte Finish:
· Blend Zelik XL ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4









For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com



HYDE PARK HEXAGON - 2" MATTE & IRIDIS

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	< 0.42
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Hexagon 2" Matte & Iridis Finish:

· Stone Glass Opalo Black XL ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com

HYDE PARK HEXAGON - 2" MATTE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	5
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	≥ 0.62
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park 2" Hexagon Matte Finish:

· Matte Black Rock XL · Matte Calacatta XL · Matte Fosco XL · Matte Ivet XL · Matte Venato White XL ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation









V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com

HYDE PARK HEXAGON - 2" SATIN

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	5
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	≥ 0.42
 Shade Variation	See Below	Substantial Variation	V4

Colors Featured in Hyde Park Hexagon 2" Satin Finish:

· Arlet XL · Bittor XL · Carel XL · Danae XL · Eloa XL · Yadel XL ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4









For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com



HYDE PARK HEXAGON - 2" STONE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	9
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	≥ 0.42
 Shade Variation	See Below	Slight Variation	V2

Colors Featured in Hyde Park Hexagon 2" Stone Finish:

· Stone Blend Soft XL · Stone Glass Black XL · Stone Glass Gainesboro XL · Stone Glass White XL ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4

For the best product laying results, material from at least three boxes should be mixed.









HYDE PARK

www.bfceramics.com

2005 International Parkway Fredericksburg, VA 22406 | Phone: 540-286-3000 | Fax: 540-286-3010



HYDE PARK HEXAGON - 2" MATTE, IRIDIS & STONE

QUALITY CHARACTERISTICS	NORM	STANDARDS	RESULT
 Water absorption of the body	ISO 10545-3	ISO 10545-3	None
 Breaking strength	ISO 10545-4		
 Abrasion resistance	ISO 10545-7	MOHS	4
 Frost resistance	ISO 10545-12	ISO 10545-12	Resistant
 Chemical resistance	ISO 10545-13	Domestic Products Pool Water Additives Low Acid + Alkalins High Acid + Alkalins	GA GA GLA GHA
 Thermal shock resistance	ISO 10545-9	ISO 10545-9	Resistant
 Dynamic coefficient of friction	BOT 3000E	ANSI A 137.1	< 0.42
 Shade Variation	See Below	Substantial Variation	V2

Colors Featured in Hyde Park Hexagon 2" Matte, Iridis & Stone Finish:
· Fossil XL ·



Uniform appearance

V1



Slight Variation

V2



Moderate Variation

V3



Substantial Variation

V4

For the best product laying results, material from at least three boxes should be mixed.

HYDE PARK

www.bfceramics.com